



US010414957B2

(12) **United States Patent**
Mansour et al.

(10) **Patent No.:** **US 10,414,957 B2**
(45) **Date of Patent:** **Sep. 17, 2019**

(54) **LOW APPLICATION TEMPERATURE HOT MELT ADHESIVE COMPOSITION**

(71) Applicant: **H.B. Fuller Company**, St. Paul, MN (US)

(72) Inventors: **Ameara S. Mansour**, Woodbury, MN (US); **Kevin P. Davis**, Woodbury, MN (US); **David B. Malcolm**, Maplewood, MN (US); **Mark S. Kroll**, Arden Hills, MN (US); **Steven R. Vaughan**, Lake Elmo, MN (US); **Timothy W. Roska**, Forest Lake, MN (US); **Evan Yuan**, Guangzhou (CN)

(73) Assignee: **H.B. Fuller Company**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 439 days.

(21) Appl. No.: **15/071,959**

(22) Filed: **Mar. 16, 2016**

(65) **Prior Publication Data**
US 2016/0272856 A1 Sep. 22, 2016

Related U.S. Application Data

(60) Provisional application No. 62/133,784, filed on Mar. 16, 2015.

(51) **Int. Cl.**
A61F 13/15 (2006.01)
C09J 153/02 (2006.01)
B32B 7/12 (2006.01)
A61L 15/24 (2006.01)
A61L 15/58 (2006.01)
B32B 27/06 (2006.01)
B32B 27/08 (2006.01)
B32B 27/10 (2006.01)
B32B 27/12 (2006.01)
C09J 7/38 (2018.01)

(52) **U.S. Cl.**
CPC **C09J 153/02** (2013.01); **A61L 15/24** (2013.01); **A61L 15/58** (2013.01); **B32B 7/12** (2013.01); **B32B 27/06** (2013.01); **B32B 27/08** (2013.01); **B32B 27/10** (2013.01); **B32B 27/12** (2013.01); **C09J 7/387** (2018.01); **B32B 2270/00** (2013.01); **B32B 2274/00** (2013.01); **B32B 2405/00** (2013.01); **B32B 2555/02** (2013.01); **C09J 2201/606** (2013.01); **C09J 2201/61** (2013.01); **C09J 2201/622** (2013.01); **C09J 2205/114** (2013.01); **C09J 2425/00** (2013.01); **C09J 2453/00** (2013.01)

(58) **Field of Classification Search**

CPC .. **C09J 153/02**; **C09J 7/0221**; **C09J 2201/606**; **C09J 2201/61**; **C09J 2201/622**; **C09J 2205/114**; **C09J 2453/00**; **A61L 15/58**; **B32B 7/12**; **B32B 27/06**; **B32B 27/08**; **B32B 27/10**; **B32B 27/12**; **B32B 2270/00**; **B32B 2274/00**; **B32B 2405/00**; **B32B 2555/02**

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,231,635 A	1/1966	Geoffrey et al.
3,239,478 A	3/1966	Harlan, Jr.
5,405,903 A	4/1995	Westrenen et al.
5,736,612 A	4/1998	Van Dongen et al.
6,162,859 A	12/2000	Lu
6,531,544 B1 *	3/2003	Vaughan A61L 24/043 525/89
6,582,829 B1	6/2003	Quinn et al.
6,818,093 B1	11/2004	Tall et al.
7,288,590 B2	10/2007	Lechat et al.
7,309,522 B2	12/2007	Webb et al.
7,439,301 B2	10/2008	Handlin, Jr.
7,795,336 B2	9/2010	Paul et al.
7,799,863 B2	9/2010	He et al.
8,129,464 B2	3/2012	Abba et al.
8,163,824 B2	4/2012	Okazaki et al.
8,324,309 B2	12/2012	Dubois
2005/0182183 A1	8/2005	He et al.
2007/0117934 A1	5/2007	He et al.
2013/0202787 A1	8/2013	Hu et al.
2013/0225020 A1	8/2013	Flood et al.
2013/0225752 A1	8/2013	Tse et al.
2014/0364532 A1	12/2014	Dubois et al.

FOREIGN PATENT DOCUMENTS

EP	0451919	2/1995
EP	1761602	6/2012
WO	WO 96/11236	4/1996

OTHER PUBLICATIONS

Kraton Innovations, "MD1648:A New Addition to the Kraton™ ERS Polymer Family", Market Launch Package, May 2014 , pp. 1-20.
"Section III: Physical Properties of Monomers and Solvents," Polymer Handbook, By E.H. Immergut et al., 4th Ed., Wiley, 2005, pp. 34-36.(Year:2005).

(Continued)

Primary Examiner — Jacqueline F Stephens
(74) *Attorney, Agent, or Firm* — Kirsten Stone; Kristi Halloran

(57) **ABSTRACT**

This invention claims low application temperature hot melt adhesive compositions including at least about 15% by weight of a first styrene block copolymer with a melt flow rate of at least about 15 g/10 minutes (190° C., 2.16 kgs) and a diblock content of no greater than about 10% by weight.

20 Claims, No Drawings