



US006797385B2

(12) **United States Patent**  
**Hart et al.**

(10) **Patent No.: US 6,797,385 B2**  
(45) **Date of Patent: Sep. 28, 2004**

(54) **POWDER COATING OF COOH ACRYLIC RESIN, POLYEPOXIDE AND LOW T CATALYST**

(75) Inventors: **Stephen C. Hart**, Hudson, WI (US); **Jeffrey G. Schmierer**, Oakdale, MN (US); **Brian W. Carlson**, Woodbury, MN (US); **Stephen C. Larson**, St. Paul, MN (US)

(73) Assignee: **H. B. Fuller Licensing & Financing Inc.**, St. Paul, MN (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 58 days.

(21) Appl. No.: **10/241,600**

(22) Filed: **Sep. 11, 2002**

(65) **Prior Publication Data**

US 2003/0069355 A1 Apr. 10, 2003

**Related U.S. Application Data**

(63) Continuation of application No. 09/579,621, filed on May 26, 2000, now Pat. No. 6,479,585.

(51) **Int. Cl.**<sup>7</sup> ..... **B32B 21/08**; B08B 27/10; C08L 33/02; C08L 33/14; C08L 63/00

(52) **U.S. Cl.** ..... **428/413**; 428/418; 428/463; 428/511; 525/108; 525/111; 525/119; 525/207; 525/208

(58) **Field of Search** ..... 428/413, 418, 428/511, 463; 525/108, 111, 119, 207, 208

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,027,066 A \* 5/1977 Victorius ..... 428/334

4,921,913 A \* 5/1990 Pettit, Jr. .... 525/119  
4,990,587 A 2/1991 Shaw et al. .... 528/113  
5,189,118 A \* 2/1993 Waddill et al. .... 525/504  
5,202,382 A \* 4/1993 Pettit, Jr. .... 525/108  
5,244,944 A 9/1993 Bott et al. .... 523/461  
5,250,634 A \* 10/1993 Toyoda et al. .... 525/438  
5,547,757 A \* 8/1996 Swarup et al. .... 428/413  
5,686,185 A \* 11/1997 Correll et al. .... 428/418  
5,721,052 A \* 2/1998 Muthiah et al. .... 428/413  
5,744,522 A \* 4/1998 Prucnal et al. .... 523/442  
5,907,020 A \* 5/1999 Correll et al. .... 525/526  
6,022,927 A \* 2/2000 Decker et al. .... 525/111  
6,245,839 B1 \* 6/2001 Jolley et al. .... 524/86  
6,296,939 B1 \* 10/2001 Kunze et al. .... 428/413

**FOREIGN PATENT DOCUMENTS**

DE 35 45 061 6/1987  
DE 196 22 921 12/1997  
EP 0 600 546 6/1994  
FR 2263265 A \* 11/1975 ..... C07B/00/00  
GB 1467052 A \* 3/1977 ..... C07B/00/00  
GB 2312897 A \* 11/1997 ..... C09D/163/00  
JP 55102672 A \* 8/1980 ..... C09J/7/04

\* cited by examiner

*Primary Examiner*—Robert Sellers

(74) *Attorney, Agent, or Firm*—Bin Su

(57) **ABSTRACT**

A powder coating composition for heat-sensitive substrates curable at a temperature of about 300° F. or below for about 30 minutes or less comprises

- a) from about 10–90% by weight, relative to a) plus b), of carboxylic acid-functional acrylic resin(s); b) from about 10–90% by weight, relative to a) plus b), of polyepoxy resin(s); c) a catalyst in an amount sufficient to cure the composition at a temperature of about 300° F. or below for about 30 minutes or less; and d) optionally, a flexibilizing agent.

**26 Claims, No Drawings**