



US007034075B1

(12) **United States Patent**  
**Torborg et al.**

(10) **Patent No.:** **US 7,034,075 B1**  
(45) **Date of Patent:** **Apr. 25, 2006**

(54) **LOW GLOSS POWDER COATING COMPOSITIONS**

(75) Inventors: **Charles J. Torborg**, Blaine, MN (US);  
**Jeffrey G. Schmierer**, Centerville, MN (US)

(73) Assignee: **H. B. Fuller Licensing & Financing Inc.**, St. Paul, MN (US)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 681 days.

(21) Appl. No.: **09/724,493**

(22) Filed: **Nov. 28, 2000**

(51) **Int. Cl.**  
**C08L 67/06** (2006.01)

(52) **U.S. Cl.** ..... **525/170; 525/934; 525/208**

(58) **Field of Classification Search** ..... **525/170, 525/934, 208**

See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,242,253	A	12/1980	Yallourakis	
4,419,495	A	12/1983	Davis	
5,436,311	A *	7/1995	Hoebeke et al.	525/174
5,491,202	A	2/1996	Umehara et al.	
5,543,464	A *	8/1996	Decker et al.	525/176
5,684,067	A	11/1997	Muthiah et al.	
5,744,522	A	4/1998	Prucnal et al.	

6,093,774	A	7/2000	Dumain	
6,296,939	B1 *	10/2001	Kunze et al.	428/413
6,407,181	B1 *	6/2002	Daly et al.	525/408
6,555,226	B1 *	4/2003	Kulzick et al.	428/413

**FOREIGN PATENT DOCUMENTS**

EP	0 465 176	1/1992
JP	07048529	2/1995
JP	07188587	7/1995
JP	11080606	3/1999
WO	WO 94/01504	1/1994
WO	WO 94/01505	1/1994
WO	WO 01/16238	3/2001

\* cited by examiner

*Primary Examiner*—Margaret G. Moore

(74) *Attorney, Agent, or Firm*—Bin Su

(57) **ABSTRACT**

The invention is directed to a low gloss powder coating composition comprising a first component (a) and a second component (b). The first component (a) comprises a mixture of (i) at least one glycidyl group-containing acrylic resin having epoxide equivalent weight of from about 250 to about 1500 and glass transition temperature of from about 30° C. to about 80° C.; and (ii) a curing agent. The second component (b) comprises at least one carboxyl-group containing material having acid number of from about 10 to about 300 and is not substantially compatible with the first component (a). The two components are dry-blended to obtain the powder coating composition.

**24 Claims, No Drawings**