



US007138437B2

(12) **United States Patent**
Giorgini et al.

(10) **Patent No.:** **US 7,138,437 B2**
(45) **Date of Patent:** **Nov. 21, 2006**

(54) **POLYURETHANE COMPOSITION
CONTAINING A PROPERTY-ENHANCING
AGENT**

(75) Inventors: **Albert A. Giorgini**, Lino Lakes, MN
(US); **Charles J. Torborg**, Blaine, MN
(US)

(73) Assignee: **H. B. Fuller Licensing & Financing
Inc.**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 89 days.

(21) Appl. No.: **10/379,625**

(22) Filed: **Mar. 4, 2003**

(65) **Prior Publication Data**

US 2004/0176490 A1 Sep. 9, 2004

(51) **Int. Cl.**

C08K 5/01 (2006.01)
C08J 9/04 (2006.01)

(52) **U.S. Cl.** **521/101**; 104/307; 521/137;
521/155; 521/170; 524/59; 524/64; 524/66;
525/123; 525/129; 525/453; 525/455; 525/457;
525/458

(58) **Field of Classification Search** 521/101,
521/137, 155, 170; 524/59, 64, 66; 525/123,
525/129, 453, 455, 457, 458; 104/307
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,886,774 A 5/1959 Probus
3,054,755 A 9/1962 Windemuth et al.
3,073,802 A 1/1963 Windemuth et al.
3,350,332 A * 10/1967 Hardy et al. 525/127
3,968,657 A * 7/1976 Hannay 405/232

3,984,493 A * 10/1976 Kazama et al. 525/129
4,080,357 A * 3/1978 Gergen et al. 524/505
4,134,546 A * 1/1979 Dankert 238/370
4,156,440 A * 5/1979 Katoh et al. 238/2
4,295,259 A 10/1981 Rhodes et al.
4,394,462 A * 7/1983 Pusineri et al. 521/137
4,408,026 A * 10/1983 Pusineri et al. 525/128
4,567,236 A * 1/1986 Goldwasser et al. 525/127
4,584,233 A * 4/1986 Meader 442/151
4,661,532 A 4/1987 Morin
5,360,871 A * 11/1994 Iwanaga et al. 525/131
5,556,934 A 9/1996 Hagquist et al.
5,929,153 A * 7/1999 Mori et al. 524/399
5,952,053 A 9/1999 Colby
5,952,072 A 9/1999 Colby et al.
6,288,133 B1 9/2001 Hagquist
6,455,605 B1 9/2002 Giorgini et al.

OTHER PUBLICATIONS

Sax et al.; *Hawley's Condensed Chemical Dictionary*, Eleventh
Edition; Van Nostrand Reinhold; New York; 1987; p. 290.*

* cited by examiner

Primary Examiner—Rabon Sergent

(57) **ABSTRACT**

A composition comprising at least a part A and a part B is disclosed. The part A comprises at least one polyol and the part B comprises at least one isocyanate. At least one part further comprises at least one of the following: a strength enhancer having a softening point of from about 120° F. to about 400° F.; a non-reactive hydrophobic enhancer; and/or an impact absorption enhancer. These enhancers provide, among optional other benefits, enhanced pull strength. Additionally, a mass can be prepared by a method of combining part A with part B and applying the mixture to a void. The compositions may also be used in the repair of surface defects or for the reinforcement of structural members such as spike holes left after spike removal from railroad ties during road bed maintenance or repair.

12 Claims, No Drawings