



US007754334B2

(12) **United States Patent**
Bushendorf et al.

(10) **Patent No.:** **US 7,754,334 B2**
(45) **Date of Patent:** ***Jul. 13, 2010**

(54) **LAMINATING ADHESIVE, LAMINATE INCLUDING THE SAME, AND METHOD OF MAKING A LAMINATE**

(75) Inventors: **Paula Bushendorf**, Woodbury, MN (US); **Peter A. Voss**, North St. Paul, MN (US)

(73) Assignee: **H.B. Fuller Company**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **12/048,934**

(22) Filed: **Mar. 14, 2008**

(65) **Prior Publication Data**

US 2008/0160319 A1 Jul. 3, 2008

Related U.S. Application Data

(63) Continuation of application No. 10/934,266, filed on Sep. 3, 2004, now Pat. No. 7,368,171.

(51) **Int. Cl.**
B32B 27/40 (2006.01)
C08F 2/46 (2006.01)

(52) **U.S. Cl.** **428/423.1; 427/208.4; 427/487; 156/331.7**

(58) **Field of Classification Search** **427/207.1, 427/519, 208.4, 487; 428/423.1, 423.5, 423.7, 428/424.8; 528/49, 75, 905; 156/331.7**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,284,731 A 8/1981 Moser et al.
4,297,185 A 10/1981 Chevreux et al.
4,352,723 A 10/1982 Morgan
4,740,577 A 4/1988 DoVoe et al.
4,756,968 A 7/1988 Ebe et al.
4,775,719 A 10/1988 Markevka et al.
4,914,173 A 4/1990 Ansell
5,013,631 A 5/1991 Su
5,021,507 A 6/1991 Stanley et al.
5,212,210 A 5/1993 Halm
5,248,752 A * 9/1993 Argyropoulos et al. 528/49
5,478,427 A 12/1995 Huver et al.
5,494,960 A 2/1996 Rolando et al.
5,703,158 A 12/1997 Duan et al.
5,741,872 A 4/1998 Smith

5,900,457 A 5/1999 Duan et al.
6,017,998 A 1/2000 Duan et al.
6,074,755 A 6/2000 Rasmussen et al.
6,093,778 A 7/2000 Pocius
6,235,384 B1 5/2001 Voss et al.
6,248,815 B1 6/2001 Papsin et al.
6,274,674 B1 8/2001 Chang et al.
6,334,710 B1 1/2002 Kuge et al.
6,465,076 B2 10/2002 Larson et al.
6,482,869 B1 11/2002 Bolte et al.

FOREIGN PATENT DOCUMENTS

EP 0 108 630 A2 5/1984
EP 0 437 944 B1 7/1991
EP 0 646 632 A1 4/1995
EP 0 666 275 B1 8/1995
EP 0 801 086 A1 10/1997
JP 05 077862 A 3/1993
JP 6-49429 2/1994
WO WO 98/33845 A1 8/1998
WO WO 98/53008 A1 11/1998
WO WO 99/23130 A1 5/1999
WO WO 01/02507 A1 1/2001
WO WO 01/05846 A1 1/2001
WO WO 02/34858 A1 5/2002

OTHER PUBLICATIONS

Shiraishi, Katsutoshi, "EB Curable Urethane Acrylate Oligomers for PSA", (1 page).

Lapsin, Stephen, "Electron Beam-Curable Laminating Adhesives for Flexible Packaging", RadTech Report, Jul./Aug. 2001, pp. 32 thru 35.

Bean, Anthony, "Energy Curing for Flexible Packaging", 1998 Polymers, Laminations & Coatings Conference, pp. 1049 thru 1055.

Henke, Gunter, "Electron-Beam Laminating Adhesives", (5 pages).

Kobayashi, Masahide, "EB Curable Laminating Adhesives for Flexible Packaging", (pp. 362 thru 369).

Shin et al., "Moisture-Resistant Anaerobic Adhesive Compositions", Chemical Abstracts, vol. 113, No. 10, Sep. 3, 1990, Columbus, Ohio, US, Abstract No. 80112c; p. 85.

* cited by examiner

Primary Examiner—Thao T. Tran

(57) **ABSTRACT**

Disclosed is a method of making a laminate that includes a) preparing an adhesive composition, where the preparing includes combining a first part that includes (meth)acrylate functional, polyisocyanate prepolymer, and polyisocyanate monomer, the first part including at least 10% by weight isocyanate functional groups, and a second part that includes polyol, at least one of the first part and the second part includes photoinitiator, b) coating a first flexible substrate with the adhesive composition, c) exposing the adhesive composition to radiation to partially cure the adhesive composition, and d) contacting the adhesive composition with a second flexible substrate.

18 Claims, No Drawings