



US007781069B2

(12) **United States Patent**
Ahmed et al.

(10) **Patent No.:** **US 7,781,069 B2**
(45) **Date of Patent:** ***Aug. 24, 2010**

(54) **MOISTURE VAPOR PERMEABLE FILM INCLUDING ETHYLENE COPOLYMER AND ARTICLES INCLUDING THE SAME**

(75) Inventors: **Sharf U. Ahmed**, Woodbury, MN (US); **Peter Remmers**, Hamburg (DE); **Andualem W. Emiru**, Woodbury, MN (US); **Joachim Baumung**, Deutsch Evern (DE)

(73) Assignee: **H.B. Fuller Company**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 44 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **12/142,010**

(22) Filed: **Jun. 19, 2008**

(65) **Prior Publication Data**
US 2008/0254270 A1 Oct. 16, 2008

Related U.S. Application Data
(63) Continuation of application No. 10/350,476, filed on Jan. 24, 2003, now Pat. No. 7,405,009.

(51) **Int. Cl.**
B32B 27/00 (2006.01)
B32B 27/08 (2006.01)

(52) **U.S. Cl.** **428/500**; 428/219; 428/515

(58) **Field of Classification Search** None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,842,741 A 6/1989 Coughlin et al.
7,405,009 B2 * 7/2008 Ahmed et al. 428/522
2003/0024881 A1 2/2003 Kalthod

FOREIGN PATENT DOCUMENTS

JP 56-156086 4/1983

* cited by examiner

Primary Examiner—Sheeba Ahmed

(57) **ABSTRACT**

A continuous film that includes ethylene copolymer selected from the group consisting of ethylene vinyl acetate, ethylene n-butylacrylate carbon monoxide, ethylene vinyl acetate carbon monoxide, and combinations thereof. The film exhibits a moisture vapor transmission rate of at least 100 g/m²/day when measured according to MVTR Test Method I.

20 Claims, No Drawings