



US007914895B2

(12) **United States Patent**
Reid

(10) **Patent No.:** **US 7,914,895 B2**
(45) **Date of Patent:** **Mar. 29, 2011**

(54) **MOISTURE CURABLE HOT MELT
ADHESIVE COMPOSITION**

(75) Inventor: **Kevin J. Reid**, White Bear Lake, MN
(US)

(73) Assignee: **H.B. Fuller Company**, St. Paul, MN
(US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 978 days.

(21) Appl. No.: **11/805,777**

(22) Filed: **May 24, 2007**

(65) **Prior Publication Data**

US 2008/0292902 A1 Nov. 27, 2008

(51) **Int. Cl.**
B32B 27/40 (2006.01)
C08G 18/61 (2006.01)

(52) **U.S. Cl.** **428/423.1**; 428/424.6; 428/424.8;
526/935; 156/332

(58) **Field of Classification Search** 428/500,
428/424.6, 424.8, 423.1; 526/935; 156/332;
525/101, 173, 451

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,618,651	A	10/1986	Gilch et al.	
4,808,255	A	2/1989	Marhevka et al.	
5,472,785	A	12/1995	Stobble, IV	
5,536,805	A	7/1996	Kangas	
6,355,317	B1 *	3/2002	Reid et al.	428/34
6,387,449	B1	5/2002	Reid et al.	
6,803,412	B2	10/2004	Nguyen-Misra et al.	
7,112,631	B2 *	9/2006	Zhang et al.	525/127
7,267,878	B2 *	9/2007	Primke et al.	428/423.1
2004/0180155	A1	9/2004	Nguyen-Misra	
2005/0143549	A1	6/2005	Schijndel	
2006/0210808	A1	9/2006	Hung et al.	

FOREIGN PATENT DOCUMENTS

GB	1 290 489	9/1972
JP	2006037037	2/2006

* cited by examiner

Primary Examiner — Thao T. Tran

(57) **ABSTRACT**

A moisture curable hot melt adhesive composition includes a polyurethane prepolymer, optionally a tackifying resin, and optionally a thermoplastic polymer. The polyurethane prepolymer includes a reaction product of an amorphous polyester polyol, a polyisocyanate, and a crystalline monofunctional alcohol that has a melting point of no less than about 80° C.

19 Claims, No Drawings