



US009522213B2

(12) **United States Patent**
Davis et al.

(10) **Patent No.:** **US 9,522,213 B2**
(45) **Date of Patent:** **Dec. 20, 2016**

(54) **PRESSURE-SENSITIVE HOT MELT ADHESIVE COMPOSITION INCLUDING PROPYLENE THERMOPLASTIC ELASTOMER AND ARTICLES INCLUDING THE SAME**

(71) Applicant: **H.B. Fuller Company**, St. Paul, MN (US)

(72) Inventors: **Kevin P. Davis**, North St. Paul, MN (US); **Ryan T. Gleason**, Shoreview, MN (US); **Peter Remmers**, Hamburg (DE)

(73) Assignee: **H.B. Fuller Company**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 207 days.

(21) Appl. No.: **13/920,347**

(22) Filed: **Jun. 18, 2013**

(65) **Prior Publication Data**

US 2014/0371703 A1 Dec. 18, 2014

(51) **Int. Cl.**

A61F 13/15 (2006.01)
A61L 15/58 (2006.01)
G09F 3/02 (2006.01)
A61F 13/56 (2006.01)
A61L 15/22 (2006.01)
C09J 7/04 (2006.01)
C09J 123/16 (2006.01)
C09J 7/02 (2006.01)
A61F 13/00 (2006.01)

(52) **U.S. Cl.**

CPC **A61L 15/585** (2013.01); **A61F 13/5611** (2013.01); **A61L 15/225** (2013.01); **C09J 7/021** (2013.01); **C09J 7/045** (2013.01); **C09J 123/16** (2013.01); **G09F 3/02** (2013.01); **A61F 2013/00757** (2013.01); **A61L 2420/06** (2013.01); **C08L 2207/04** (2013.01); **C09J 2400/163** (2013.01); **C09J 2400/226** (2013.01); **C09J 2400/263** (2013.01); **C09J 2423/10** (2013.01); **G09F 2003/0241** (2013.01); **Y10T 428/1476** (2015.01); **Y10T 428/2804** (2015.01); **Y10T 428/2878** (2015.01); **Y10T 442/2754** (2015.04)

(58) **Field of Classification Search**

CPC **A61F 2013/00748**; **A61F 2013/00757**
USPC **604/366, 372, 373**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,987,122 A 10/1976 Bartz et al.
5,418,052 A * 5/1995 Sugie C09J 153/025
428/335

6,143,818 A 11/2000 Wang et al.
6,489,400 B2 12/2002 Khandpur et al.
6,657,000 B1 12/2003 De Keyzer et al.
6,747,114 B2 6/2004 Karandinos et al.
6,833,404 B2 12/2004 Quinn et al.
6,872,279 B1 3/2005 Kolowrot et al.
7,199,180 B1 4/2007 Simmons et al.
7,294,681 B2 11/2007 Jiang et al.
7,521,507 B2 4/2009 Lewtas et al.
7,700,707 B2 4/2010 Abhari et al.
7,989,543 B2 8/2011 Karjala et al.
2003/0096896 A1 5/2003 Wang et al.
2007/0135563 A1 6/2007 Simmons et al.
2007/0202330 A1 * 8/2007 Peng C08L 23/04
428/375
2008/0076860 A1 * 3/2008 Ahmed et al. 524/275

FOREIGN PATENT DOCUMENTS

EP 0 178 062 4/1986
EP 1 700 895 9/2006
WO WO 00/01745 1/2000
WO WO 2011/022523 2/2011
WO WO2012/129489 9/2012

OTHER PUBLICATIONS

Eastman Chemical Company, "Eastotac H-142w Resin" (Apr. 2, 2012) (2 pages).
ExxonMobil Chemical, "Vistamaxx 6102 Propylene-based Elastomer" (Revised Jan. 22, 2013) (2 pages).
ExxonMobil Chemical, "Vistamaxx 6202 Propylene-based Elastomer" (Revised Jan. 22, 2013) (2 pages).
ExxonMobil Chemical, "Escorez 5400 Tackifying Resin" (Date Unknown) (1 page).
Eastman Chemical Company, "Eastotac H-130W Resin" (Apr. 2, 2012) (2 pages).
ExxonMobil Chemical, "Vistamaxx 3000 Propylene-based Elastomer" (Revised Jan. 22, 2013) (2 pages).
Kraton Polymers, "Kraton G1657 M Polymer" (Jul. 31, 2009) (2 pages).
ExxonMobil Chemical, "Escorez 2510 Tackifying Resin" (Dec. 2006) (1 page).
Eastman Chemical Company, "Piccotac 1115 Hydrocarbon Resin" (Aug. 14, 2006) (2 pages).
ExxonMobil Chemical, "Vistamaxx 3980FL Propylene-based Elastomer" (Revised Jan. 22, 2013) (2 pages).

* cited by examiner

Primary Examiner — Jacqueline Stephens

(74) Attorney, Agent, or Firm — Kirsten Stone; Allison Johnson

(57) **ABSTRACT**

A pressure-sensitive hot melt adhesive composition is disclosed that includes at least 10% by weight of a first propylene thermoplastic elastomer, at least 25% by weight of a first tackifying agent exhibiting a softening point of at least 120° C., and at least 25% by weight plasticizer.

38 Claims, No Drawings